

PRODUCT DATA SHEET

Description

E222 is a 2 component low viscosity epoxy used as a flowable grout, ideally suited to a wide range of building and civil engineering applications. The product bonds to steel and concrete and is simple to mix and apply.

Principal uses

- As a resin for chemical anchoring
- As a liquid grouting or chocking medium
- Fixing starter bars, bolts and other similar items, vertically down into concrete

Advantages

- Superior adhesion to most masonry materials
- Stronger than surrounding concrete and steel
- High strength and High modulus
- Chemical resistance
- Heat resistance characteristics

Performance data

Product complies to ASTM C881

Adhesion to sandblasted steel	11 Mpa
Tensile strength	>22 Mpa
Compressive strength	74Mpa
Adhesion to concrete	concrete failure

Surface preparation

Remove all dust from holes, any loose material, rust and any oil based residue where the product will be applied. All surfaces must be clean, sound and dry. Pockets must be free of standing water.

Pot life & Curing

The product has a 30 minute pot life at an ambient temperature of 25°C. Should the temperature increase, expect an accelerated reaction. In typical applications the product will be touch dry in 6 hours and fully cured in 7 days.

Application

Mixing- using a small trowel, mix component A with component B for 3 minutes or until uniform colour is achieved

Application- pour enough material into the hole to ensure that once the bar is placed the material will push up to the top. Ensure that air entrapment does not take place

Yield

$0,8 (D+d)(D-d) HN = \text{Litres of grout}$

1 000 required

Where;

D = diameter of hole in cm

d = diameter of metal in cm

H = depth of hole in cm

N = number of holes

ANCHORING METHOD

Bar Diameter	Hole Diameter	Depth required
8	10	120
10	12	150
12	15	180
16	20	240
20	25	300
25	32	375
32	40	480
40	50	600

IMPORTANT NOTES

- Depth of hole should be 15 times diameter of the rod or bar.
- Diameter of hole should be 1.25 to 1.5 times diameter of the rod or bar.
- Do not split kits or part mix

Limitation

Working temperature between 5-35°C

Ensure that no air entrapment occurs

Maximum service temperature 70°C

Safety & Handling

Note: The information and specifications provided is to the best of our knowledge. The technical data contained herein are true and accurate at the date of issue and are subject to change without prior notice. No guarantee of accuracy is given or implied. We guarantee our products to conform to Epoxerite quality control. We cannot be held responsible or liable, directly or in indirectly for the use of our products, coverage, performance or injury resulting from use, as we have no control over the method of application used or site conditions. For further technical and method statements, contact our Technical representatives.

Epoxy resin components may cause skin irritation. The product is low in acute oral toxicity. At room temperature, there is exposure to vapours from the product that may cause allergic skin reaction in humans. Safe handling can best be accomplished by adhering to the following rules:

- Work in well ventilated areas
- Wear PVC gloves, safety glasses and aprons
- Remove any residue with soap and water
- In the event of contact with eyes flush with copious amounts of water. Seek immediate medical attention
- Prior to mixing and curing the product is harm full to the environment

Packaging

The product is a 2 component kit

The following kit sizes are available; 1ℓ, 2ℓ and 5ℓ

Shelf life & storage instructions

12 months when stored in a cool dry place, failure to comply with these recommendations will result in a reduction in shelf life

Note

For further instruction please consult your local representative for a method statement on the product

Note: The information and specifications provided is to the best of our knowledge. The technical data contained herein are true and accurate at the date of issue and are subject to change without prior notice. No guarantee of accuracy is given or implied. We guarantee our products to conform to ASHAKepoxerite Products quality control. We cannot be held responsible or liable, directly or in directly for the use of our products, coverage, performance or injury resulting from use, as we have no control over the method of application used or site conditions. For further technical and method statements, contact our Technical representatives.