

PRODUCT DATA SHEET

Description

CCW20 is a wax based curing compound that complies to ASTM C309 – 2005

Principal uses

CCW20 is a membrane forming wax emulsion curing compound which, when applied to damp concrete, seals in moisture, arrests evaporation and ensures adequate hydration right to the surface of the concrete for an off- shutter finish Where a finish is to be applied to the concrete afterwards e.g.Plaster, Paint or tiling, it is recommended that you use CCR10 (Resin based curing compound).

CCW20 IS NOT SUITABLE FOR OFF-SHUTTER CONCRETE.

The curing compound will eventually break down where it is exposed to direct sunlight, but this could take at least 12 months to happen should you decide to put a finish onto the surface later

Application

Apply CCW20 by paint roller, brush or low pressure spray as soon as no surface sheen or bleed water remains. The spray nozzle should be held approximately 450mm from the surface.

Performance data

Appearance:	Milky white
Temperature stability:	Stable
Flash point:	Nil
Odour:	Slight
Physical form:	Liquid

Coverage

Coverage is 4 to 6 square metres per litre depending on concrete texture and ambient conditions. For very smooth concrete use the higher coverage rate.

Packaging

CCW20 is available in 25 ℓ and 210ℓ drums

Safety & handling

Use gloves and eye protection at all times. Should the product come into contact with eyes, wash immediately and seek medical advice

Shelf Life & Storage

12 months when stored in a cool dry place, failure to comply with these recommendations will result in a reduction in shelf life

Note

Roll drum before use to prevent settling out of the product

Note: The information and specifications provided is to the best of our knowledge. The technical data contained herein are true and accurate at the date of issue and are subject to change without prior notice. No guarantee of accuracy is given or implied. We guarantee our products to conform to Epoxerite quality control. We cannot be held responsible or liable, directly or in indirectly for the use of our products, coverage, performance or injury resulting from use, as we have no control over the method of application used or site conditions. For further technical and method statements, contact our Technical representatives.